

don't n.e
understand
2.

Continue with the existing text as a separate paragraph, starting at Page 10, line 22.

In the claims:

SUBB2)
Claim 5 (Amended) - Product (1) as claimed in [one of the preceding claims] Claim 2, characterized in that the spinel is present as a mixture in the ternary system of the type AB_2X_4 - AX - B_2X_3 .

0530053 1222
A2
Claim 6 (Amended) - Product (1) as claimed in [one of the preceding claims] Claim 2, characterized in that the mixed oxide system with the spinel has an additional oxide or several additional oxides.

Claim 7 (Amended) - Product (1) as claimed in [one of the preceding claims] Claim 6, characterized in that the additional oxide is stabilized with yttrium oxide (Y_2O_3) or another rare earth oxide.

SUBB3)
A3
Claim 9 (Amended) - Product (1) as claimed in [one of the preceding claims] Claim 2, characterized in that between basic body (2) and thermal barrier coating (4) a bond coat (3) forming a bonding oxide is disposed.

SUBB5)
A5
Claim 11 (Amended) - Product (1) as claimed in [one of the preceding claims] Claim 2, characterized in that it is designed as a component of a thermal turbo machine, particularly a gas turbine.

SUBB7)
A5
Claim 13 (Amended) - Product (1) as claimed in [one of the preceding claims] Claim 2, characterized in that the thermal-expansion coefficient α of the spinel is between $6 \cdot 10^{-6}/K$ and $17 \cdot 10^{-6}/K$.

~~Claim 14 (Amended) - Product (1) as claimed in [one of the preceding claims]~~

~~Claim 2, characterized in that the thermal conductivity of the spinel is between 1.0 W/mK and 4.0 W/mK.~~

~~Claim 15 (Amended) - Product (1) as claimed in [one of the preceding claims]~~

~~Claim 2, wherein the metallic basic body (4) has a nickel, cobalt and/or chromium-based super alloy.~~

Newly Added Claims

~~16. Product (1) as claimed in Claim 1, characterized in that the spinel is present as a mixture in the ternary system of the type AB_2X_4 - AX - B_2X_3 .~~

~~17. Product (1) as claimed in Claim 1, characterized in that the mixed oxide system with the spinel has an additional oxide or several additional oxides.~~

~~18. Product (1) as claimed in Claim 1, characterized in that between basic body (2) and thermal barrier coating (4) a bond coat (3) forming a bonding oxide is disposed.~~

~~19. Product (1) as claimed in Claim 1, characterized in that the thermal expansion coefficient α of the spinel is between $6 \cdot 10^{-6}/K$ and $17 \cdot 10^{-6}/K$.~~

~~20. Product (1) as claimed in Claim 1, characterized in that the thermal conductivity of the spinel is between 1.0 W/mK and 4.0 W/mK.~~

~~21. Product (1) as claimed in Claim 1, wherein the metallic basic body (4) has a nickel, cobalt and/or chromium-based super alloy.~~

In the abstract, Page 17, cancel line 11.